CLEMSON UNIVERSITY
THE BISHOP MATERIALS LABORATORY

THE BISHOP MATERIALS LABORATORY

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095

www.bishopmaterialslab.com

AASHTO R18 ACCREDITED LABORATORY

Results of Tests on Brick conducted in accordance with ASTM C67-11 Standard Method for Sampling and Testing Brick and Structural Clay Tile

02/22/2012

Name:	Palmetto Brick Company P. O. Box 430 Cheraw, SC 29520-0430	Plant:	Palmetto Brick Company
		Report Number:	PALB-0049
Phone:	843-320-1137	Sampled Date:	01/23/2012
Fax:	843-537-4802	Lot:	
		Product Code:	
Sample Description:	**Jamestown Body**		

							Test Date
Absorption	**1**	**2**	**3**	**4**	**5**	**Average**	
24 Hour Submersion in Cold Water (%)	6.45	6.59	6.56	6.18	6.46	6.45	02/01/2012
5 Hour Submersion in Boiling Water (%)	8.96	9.03	9.01	8.85	8.94	8.96	
Saturation Coefficient (Ratio of 24H to 5H)	0.72	0.73	0.73	0.70	0.72	0.72	
Compressive Strength	**1**	**2**	**3**	**4**	**5**	**Average**	
psi	13,244	12,027	11,914	12,208	12,904	12,459	02/02/2012
MPa	91.3	82.9	82.1	84.2	89.0	85.9	
Efflorescence	**11**	**12**	**13**	**14**	**15**		
	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		02/17/2012
IRA	**6**	**7**	**8**	**9**	**10**	**Average**	
g/min/30 in.²	5.5	10.0	9.5	6.6	11.5	8.6	02/02/2012
Average % Void	24.2						01/30/2012

The brick represented by the test results shown here comply with the standards listed below:

ASTM C 216 - 11 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale)
Grade: SW, MW

John Sanders, Ph.D., PE, Associate Director for Operations

Gary W. Parker, Laboratory Supervisor